



DESCO INDUSTRIES INC

926 JR INDUSTRIAL DRIVE, SANFORD, NC 27332 • PHONE (919) 718-0000 | (909) 627-9634 • StaticControl.com

QUALIFICATION REPORT – ANSI/ESD S20.20

SCS MAGSNAP 360™ DUAL-WIRE THERMOPLASTIC WRISTBAND

ANSI/ESD S20.20	SCS Test Results	Test Methods
--------------------	---------------------	--------------


Resistance (ohms), N=6 specimens, 10V-100V

Wrist Strap (Band and cord)	0.8×10^6 to 1.2×10^6	See Table 1	ANSI/ESD S1.1 (Section 6.1)
Wristband Interior	$< 1.0 \times 10^5$	See Table 1	ANSI/ESD S1.1 (Section 6.2)
Wristband Exterior	$> 1.0 \times 10^7$	See Table 1	ANSI/ESD S1.1 (Section 6.2)
Wrist Strap System	$< 3.5 \times 10^7$	See Table 1	ANSI/ESD S1.1 (Section 6.10)


Test Data:

Table 1 – Resistance (ohms)


	Sample #1	Sample #2	Sample #3	Sample #4	Sample #5	Sample #6
Wrist Strap ANSI/ESD S1.1 – Figure 2	9.86×10^5	9.93×10^5	9.93×10^5	9.93×10^5	9.82×10^5	9.82×10^5
Wristband Interior ANSI/ESD S1.1 – Figure 4	$< 1.0 \times 10^3$					
Wristband Exterior ANSI/ESD S1.1 – Figure 4	$> 1.0 \times 10^{11}$					
Wrist Strap System ANSI/ESD S1.1 – Figure 8	1.24×10^6	1.27×10^6	1.24×10^6	1.20×10^6	1.27×10^6	1.36×10^6

References:

ANSI/ESD S1.1 – Figure 2: Set-up for Wrist Strap Resistance Test



ANSI/ESD S1.1 – Figure 4: Set-up for Wristband Resistance Test



ANSI/ESD S1.1– Figure 8: Wrist Strap System Resistance Test